



Le Rocher, Mahe, Seychelles - P.O Box 368 Tel: 4344606/108 Fax: 4344373

email: penlacadmin@seychelles.sc

SUPER GLOSS ENAMEL

PRODUCT DATA SHEET

Good quality Alkyd Resin Based Gloss top coat for wood and metallic surfaces.

SUPER GLOSS ENAMEL is a general purpose decorative and protective coating used as a finishing coat for alkyd based paints systems on all types of wood and metallic surfaces. It is easy to apply and has exceptional flow properties. It dries rapidly to give a tough durable washable finish which is resistant to mild acids.

USAGE

- On suitably primed wood such as beams, panels, doors, window frames, skirting's, handrails, furniture, balustrades, roof shingles, ceilings, decorative items, wooden structures, etc.
- On suitably primed mild steel, galvanised steel or aluminium surfaces such as roofs, doors, window frames, furniture, beams, handrails, balustrades, machinery, bus and truck bodies, industrial and agricultural equipment, structural steel, etc.
- For interior and exterior application.

SUPER GLOSS ENAMEL is not suitable for surfaces which will be subjected to strong wear and tear conditions, do not use on floors, concrete, counter and table tops.

PHYSICAL DATA

- **Finish :** Gloss
- **Colour :** White, Black and Range of Colours.
- **Consistency :** Semi viscous Liquid
- **Specific Gravity :** 1.12 (approx.)
- **Volume Solids :** 45% (approx.)
- **Flash Point :** 27 °C (Closed cup)
- **Shelf Life :** 12 months
- **Packing :** 20Lts, 4Lts, 1Lt,

Paints should be stirred before use and occasionally whilst in use.
Contact your supplier for further information.

APPLICATION

- **Surface Preparation:** Wood, mild steel and galvanised steel/aluminium surfaces respectively. When applied to these surfaces it is necessary to ensure that at least one coat of Alkali resistant primer or Undercoat such as Universal undercoat, Wood Primer or Red Oxide Primer is applied beforehand.
- **Application Method:** Apply three coats by roller, brush or airless spray.
- **Dilution:** Thin down with **TEST BENZIN** as required.
- **Spreading rate / Film thickness:** One litre of Super Gloss Enamel will cover between 9 and 11 m² of surface in one coat; at this spreading rate the dry film thickness will vary between 58 and 48 microns on a completely smooth, non absorbent surface.
- **Drying Time:** Approximately 4 hours to touch dry, Super Gloss Enamel can be over-coated after approximately 16 hours.
- **Cleaning Solvent:** **TESTBENZIN**.
- **Subsequent coat:** Not required.

SAFETY

- **Super Gloss Enamel** is flammable, keep away from ignition source. Do not smoke whilst using.
- Wear adequate protective equipment during application, remove splashes from skin with soap and water. In case of contact with eyes, rinse with ample water and seek medical advice if necessary.
- Ensure good ventilation during application and drying.
- Keep containers tightly closed and away from children.
- A complete Material Safety Data Sheet is available on request.

MAINTENANCE

Surfaces prepared and painted according to specification will provide lasting protection and will facilitate maintenance. Carry out repairs as and when required and wash the surface occasionally; use mild detergent and light scrubbing to remove stains.

These recommendations are meant as a guide, no guarantee is implied since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.