



CHLORINATED SEALER - CLEAR

PRODUCT DATA SHEET

CHLORINATED SEALER is a chlorinated rubber based sealer for concrete, masonry surfaces or Wood. Applied in dilute coats on these surfaces, it provides good sealing and ensures a sound foundation for application of subsequent chlorinated rubber coatings.

USAGE

- For interior and exterior application.
- On concrete and masonry surfaces.

Note: Condensation or dew formation on metallic surfaces will result in poor adhesion and subsequent flaking of the paint. Avoid painting during early morning, late evening or during humid and wet periods.

PHYSICAL DATA

- **Product Code :** CHL
- **Finish :** Gloss
- **Colour :** Clear
- **Consistency :** Free flowing Liquid
- **Specific Gravity :** 1.0 (approx.)
- **Volume Solids :** 30% (approx.)
- **Flash Point :** < 23 °C, closed cup
- **Shelf Life :** 12 months
- **Packing :** 4 L, 1 L,

Paints should be stirred before use and occasionally whilst in use.

Contact your supplier for further information

APPLICATION

- **Surface preparation:** See method SP 001 for concrete and masonry surfaces.

Note: **CHLORINATED SEALER** contains a high level of aromatic solvent. Before over coating previously coated surfaces, compatibility should always be checked. Surfaces subject to water infiltration should not be coated with **CHLORINATED SEALER** as this may result in blistering and peeling problems.

- **Application method:** Apply one to two dilute coats by roller or brush onto clean, dry surface to ensure good penetration.
- **Dilution :** Thin down with CHLORINATED RUBBER THINNER as required.
- **Spreading rate / Film thickness :** One litre of **CHLORINATED SEALER** will cover between 8 and 10 m² of surface in one coat ; at this spreading rate the dry film thickness will vary between 37.5 and 30 microns on a completely smooth, non absorbent surface.
- **Drying time:** Approximately 30 minutes to touch dry, **CHLORINATED SEALER** can be over-coated after approximately 3 hours.
- **Cleaning solvent:** CHLORINATED RUBBER THINNER.
- **Preceding coat:** Not required.
- **Subsequent coat:** **CHLORINATED ENAMEL.** Alternatively, **CHLORINATED UNDERCOAT** followed by **CHLORINATED ENAMEL.**

SAFETY

- **CHLORINATED SEALER** is flammable, keep away from ignition source. Do not smoke whilst using.
- Wear adequate protective equipment during application, remove splashes from skin with soap and water. In case of contact with eyes, rinse with ample water and seek medical advice if necessary.
- Ensure good ventilation during application and drying.
- Keep containers tightly closed and away from children.
- A complete Material Safety Data Sheet is available on request.

MAINTENANCE

Surfaces prepared and painted according to specification will provide lasting protection and will facilitate maintenance. Carry out repairs as and when required and wash the surface occasionally; use mild detergent and light scrubbing to remove stains.

These recommendations are meant as a guide, no guarantee is implied since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.