



Le Rocher, Mahe, Seychelles - P.O Box 368 Tel: 4344606/108 Fax: 4344373

email: penlacadmin@seychelles.sc

CHLORINATED UNDERCOAT WHITE

PRODUCT DATA SHEET

A good quality chlorinated rubber based intermediate coat recommended for building-up film thickness of chlorinated rubber coating systems. It has excellent adhesion to preceding coats and provides a good foundation for the adhesion of top coats.

USAGE

- On sealed cement surfaces.
- On suitably primed mild steel, galvanised steel, aluminium surfaces, Wood and cement.
- For interior and exterior use.

Note: Condensation or dew formation on metallic surfaces will result in poor adhesion and subsequent flaking of the paint. Avoid painting during early morning, late evening or during humid and wet periods.

PHYSICAL DATA

- **Finish :** Matt
- **Colour :** White
- **Consistency :** Semi - viscous Liquid
- **Specific Gravity :** 1.24 (Approx.)
- **Volume Solids :** 30% (Approx.)
- **Flash Point :** < 23 °C, closed cup
- **Shelf Life :** 12 months
- **Packing :** 20 L, 4L, 1L ,

Paints should be stirred before use and occasionally whilst in use.
Contact your supplier for further information

APPLICATION

- **Application method:** Apply one or two coats by roller or brush onto clean, dry surface. Conventional, low pressure spray can also be used after thinning. Airless spray is also possible.
- **Dilution :** Thin down as required with :-
 - ◇ **CHLORINATED RUBBER THINNER** for roller or spray application is desirable.
- **Spreading rate / Film thickness:** One litre of **CHLORINATED UNDERCOAT** will cover between 6 and 7.5 m² of surface in one coat; at this spreading rate the dry film thickness will vary between 50 and 40 microns on a completely smooth, non absorbent surface.
- **Drying time:** Approximately 30 minutes to touch dry, **CHLORINATED UNDERCOAT** can be over-coated after approximately 3 hours.
- **Cleaning solvent :** CHLORINATED RUBBER THINNER
- **Subsequent coat :** **CHLORINATED RUBBER ENAMEL.**

SAFETY

- **CHLORINATED RUBBER UNDERCOAT** is flammable, keep away from ignition source. Do not smoke whilst using.
- Wear adequate protective equipment during application, remove splashes from skin with soap and water. In case of contact with eyes, rinse with ample water and seek medical advice if necessary.
- Ensure good ventilation during application and drying.
- Keep containers tightly closed and away from children.
- A complete Material Safety Data Sheet is available on request.

MAINTENANCE

Surfaces prepared and painted according to specification will provide lasting protection and will facilitate maintenance. Carry out repairs as and when required and wash the surface occasionally; use mild detergent and light scrubbing to remove stains.

These recommendations are meant as a guide, no guarantee is implied since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.